

Microcline - Amelia

Sample no. 6308. (from the same locality
as sample no. 6307).

SiO ₂	65.34
Al ₂ O ₃	18.74
Rb ₂ O	0.83 (flame)
K ₂ O	13.7 (fluorescence)
K ₂ O	13.56 (flame)
Na ₂ O	1.73 (flame)

N.B. This sample is perthitic - not
homogeneous.

Ref: D.R. Waldbaum, Ph.D. thesis, 1966,
p.23.