

IN STANDARD PELLET

Aegirine #17A Wabush Iron Formation, Labrador
Canada

Weight %

SiO ₂	50.80
TiO ₂	-
Al ₂ O ₃	0.20
Fe ₂ O ₃	29.43
FeO	1.98
MnO	4.30
MgO	0.81
CaO	1.73
Na ₂ O	10.37
K ₂ O	0.07
H ₂ O ⁺	0.15
H ₂ O ⁻	0.09
<hr/>	<hr/>
Total	99.93

Spectrographically detected elements
Ba, Sr, Cr, Ag, Cu, Y, Be

Ref: Klein, C., 1965 Ph.D. thesis, Harvard

Analyst: Jun Ito