

IN STANDARD PELLET

Orthopyroxene #1397 (B) Sunnøre, Norway

	Weight %
SiO <sub>2</sub>	54.29
TiO <sub>2</sub>	0.00
Al <sub>2</sub> O <sub>3</sub>	1.00
Fe <sub>2</sub> O <sub>3</sub>	-
Cr <sub>2</sub> O <sub>3</sub>	-
FeO	17.44
MnO	0.07
MgO	26.57
CaO	-
BaO	-
Na <sub>2</sub> O	0.10
K <sub>2</sub> O	tr
P <sub>2</sub> O <sub>5</sub>	-
H <sub>2</sub> O(+)	0.91
H <sub>2</sub> O(-)	
<hr/>	<hr/>
Total	100.38
NiO	0.0x
F	ND
SrO	-

ANALYST: JUN ITO

FROM: H.H. SCHMITT